



**pindo deli**  
paper products

FO/0/01/1  
Rev : 1

UNCONTROLLED COPY

SPECIFICATION		DOC. NO.	SP/6/204/1032
		REVISION	3
		DATE OF ISSUE	22/04/2009
		PAGE	1 OF 1

**TITLE : CARBONLESS PAPER CF 48, 50, 55, 60 & 75 GSM (R) IMPRESSION 2000**

NO	PARAMETER	UNIT	CF 48	CF 50	CF 55	CF 60	CF 75	TEST METHOD
1	Basis Weight	g/m <sup>2</sup>	48 ± 1	50 ± 2	52 - 56	60 ± 2	73 - 77	ISO 536: 1995
2	Thickness	micron	65 ± 2	66 ± 3	69 ± 3	77 ± 3	93 ± 3	ISO 534: 2005
3	Bendtsen Roughness	ml/min	Max. 150	Max. 150	Max. 150	Max. 150	Max. 180	ISO 8791-2: 1990
4	Copy Intensity		Max. 150	Max. 150	Max. 150	Max. 150	Max. 180	
		TS	Min. 29	Min. 29	Min. 29	Min. 29	Min. 29	
		BS	-	-	-	-	-	
		2 <sup>nd</sup> 4 <sup>th</sup> 5 <sup>th</sup> 6 <sup>th</sup>	Min. 26	Min. 26	Min. 26	Min. 26	Min. 26	

Note : TS = Top Side BS = Bottom Side  
Printer Type for Intensity : EPSON LQ - 2180 Standard Resolution 180 x 180 dpi

Prepared By:   
Sec. Head of QC  
Date: 21/4/2009

Approved By:   
Production Manager  
Date: 22/4/2009

Head of Tech. Division  
Date: 22/4/2009