



pindo deli
paper products

FO/0/01/1
Rev : 1

UNCONTROLLED COPY

SPECIFICATION		DOC. NO.	SP/6/2004/1046
		REVISION	1
		DATE OF ISSUE	22/04/2009
		PAGE	1 OF 1
TITLE : CARBONLESS PAPER CFB 50, 53, 60 & 75 GSM (R) IMPRESSION 2000			

NO	PARAMETER	UNIT	CFB 50	CFB 53	CFB 60	CFB 75	TEST METHOD
1	Basis Weight	g/m ²	47 - 51	53 ± 2	60 ± 2	72 - 76	ISO 536: 1995
2	Thickness	micron	68 ± 3	73 ± 3	82 ± 3	100 ± 3	ISO 534: 2005
3	Bendtsen Roughness	ml/min	Max. 150	Max. 150	Max. 190	Max. 200	ISO 8791-2: 1990
4	Frictional Smudge	%	Max. 500	Max. 500	Max. 500	Max. 500	-
5	Copy Intensity	%	Max. 7	Max. 7	Max. 7	Max. 7	-
		2 nd	<u>Min. 29</u>	<u>Min. 29</u>	<u>Min. 29</u>	Min. 29	-
		3 rd	-	-	-	Min. 27	-
		4 th	-	-	-	Min. 26	-
		5 th	<u>Min. 27</u>	<u>Min. 27</u>	<u>Min. 26</u>	-	-
		6 th	Min. 26	Min. 26	-	-	-

Note: TS = Top Side BS = Bottom Side Printer Type for Intensity : EPSON LQ - 2180 Standard Resolution 180 x 180 dpi

Prepared By:

[Signature]

Sec. Head of QC
Date: 21/4/2009

Approved By:

[Signature]

Production Manager
Date: 22/4/2009

[Signature]

Head of Tech. Division
Date: 22/4/2009